



# STYLE BETON

## Acid Stain

|                            |   |
|----------------------------|---|
| <p><b>DESCRIPTION</b></p>  | <p><b>Style Beton Acid Stain</b> is an acidic coloring solution of metallic salts which chemically reacts with concrete and other cementitious substrates to create translucent and variegated color effects. <b>Style Beton Acid Stain</b> resembles marble or natural stone.</p> <p>We offer 6 standard colors with which you can create an unlimited variety of shades.</p> <p>The material reacts individually with each substrate depending upon its available cement content, age, and porosity. Test the surface before application, to ensure you are satisfied with the color.</p> |
| <p><b>Colors</b></p>       | <p>6 Basic Colors. Bronze, Caramel, Coffee, Ebony, Jade, Mahogany. Unlimited variety of shades.</p>   |
| <p><b>Restrictions</b></p> | <ul style="list-style-type: none"> <li>• Different concrete pours will react differently. The stain will not hide surface defects.</li> <li>• The coloring effect is depending on individual substrate and application methods.</li> <li>• The stain will not be effective if the concrete is excessively old or has been previously sealed.</li> <li>• Testing on the individual substrate is required to determine the specific stain effect prior to beginning the project.</li> </ul>   |
| <p><b>Packaging</b></p>    | <p>1lt or 5 lt containers.</p>  |
| <p><b>Storage</b></p>      | <p>Store in a well ventilated area at room temperature.</p>   |

|                                   |   |
|-----------------------------------|---|
| <p><b>Application</b></p>         | <p>Concrete must be cured enough to become reactive with the stain. It must be free of all contaminants such as grease, adhesives and previously applied sealers. Test for presence of a sealer. Wet the surface with water. If the water is not immediately absorbed and the surface darkened, sealer is present and must be removed.</p> <p>On dry and prepared concrete surface (Nano-Top, Stamped Concrete Overlay, etc) apply Style Acid Stain with a pump sprayer and immediately scrub in circular motion with a soft brush. After first coat is thoroughly dry, a second coat should be applied the same way after 3-4 hours.</p> <p>Leave it to stay for 24 hours so to achieve the maximum coloration and hardening of the chemical reaction. Wash with water mixed with baking soda in order to neutralize the surface and rinse well with water. Allow to dry thoroughly. Seal the surface with 2 coats Style Sealer. If slip resistance is required, you may add Style Anti-Slip to the sealer.</p> <p>Interior concrete surfaces may be applied with floor wax.</p>   |
| <p><b>CLEANING</b></p>            | <p>The tools are recommended to be cleaned immediately after use with water.</p>  |
| <p><b>HEALTH AND SAFETY</b></p>   | <p>Read the label before use. Use a face mask and gloves.</p>   |
| <p><b>GENERAL INFORMATION</b></p> | <p>Note that the technical application and the experience of work teams will affect the final aesthetic result of the floor.</p> <p>The information and in particular the recommendations relating to the application and final use of products «STYLE BETON» given in good faith, based on current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual application conditions are such that no guarantee can be given in respect of merchantability or fitness for a particular purpose and no liability of any legal relationship can be established against the company based here in labeling information, written recommendations, or other advice offered. Respect the rights of others is essential. Users must always refer to the most recent version of this.</p> <div data-bbox="863 1599 1023 1778" data-label="Image"> </div> <p style="text-align: center;"><b>STYLE BETON</b></p> <p style="text-align: center;"><b>Navarinou 8, Kalochori, Thessaloniki, Greece, 57009</b><br/> <b>TEL. : 0030 2310 - 920831, FAX : 0030 2310 - 920832,</b><br/> <a href="http://www.stylebeton.com">www.stylebeton.com</a> , <a href="mailto:info@stylebeton.com">info@stylebeton.com</a></p> |